

FORMULATION



NIKKOL GROUP

COSMOS TECHICAL CENTER CO.,LTD

3-24-3 HASUNE, ITABASHIKU, TOKYO 174-0046 JAPAN

Tel 03-3966-7755 Fax 03-3966-7307

Oct 26, 2018

Formula Name : Aqua Veil Foundation

Lot.No.35-HWO-1

(NIKKOL Nikkomulse WO : 5.0%)

--	--	--

INCI NAME	TRADE NAME	SUPPLIER	wt%
A			
CAPRYLYL METHICONE	Gransil AM-8	GRANT INDUSTRIES	22.0500
CYCLOPENTASILOXANE,PEG-10 DIMETHICONE,DISTEARDIMONIUM HECTORITE	NIKKOL Nikkomulse WO	NIKKO CHEMICALS	5.0000
TITANIUM DIOXIDE,ALUMINUM HYDROXIDE,TALC,HYDROGEN	FDP-C-WHITE3	Toshiki-Pigment	9.0000
TITANIUM DIOXIDE,ALUMINUM HYDROXIDE,TALC,HYDROGEN	FDP-C-RED3	Toshiki-Pigment	1.5000
DIMETHICONE,IRON OXIDES TITANIUM DIOXIDE,ALUMINUM HYDROXIDE,TALC,HYDROGEN	FDP-C-YELLOW3	Toshiki-Pigment	3.0000
DIMETHICONE,IRON OXIDES TITANIUM DIOXIDE,ALUMINUM HYDROXIDE,TALC,HYDROGEN	FDP-C-BLACK3	Toshiki-Pigment	1.5000
DIMETHICONE,IRON OXIDES METHYL METHACRYLATE	UP-611	Toshiki-Pigment	3.0000
CROSSPOLYMER,HDI/TRIMETHYLOL HEXYLLACTONE CROSSPOLYMER			
B			
PHENOXYETHANOL			0.4000
PROPANEDIOL			4.0000
SODIUM CHLORIDE			0.5000
DISODIUM EDTA			0.0500
WATER			50.0000
		Total	100.0000
Procedure			
1. Disperse A with dispermixer until uniform.			
2. Dissolve B at room temperature.			
3. While mixing A with disper mixer add B to A gradually.			
4. Emulsify with disper mixer.			
Note			
Initial viscosity(Btype Viscometer No.4 6rpm./30sec.): 18700 mPa·s			

We do not guarantee the stability of the final products of formulations in this brochure though the stability was checked at 45°C for 12 weeks.

We do not guarantee the preservation property of this formulation as we do have not checked it.